



ETCH PRIMER

GENERIC TYPE

Two Components.

COMPOSITION

Vinyl Butaryl Resin with rust inhibitive pigmented.

RECOMMENDED USE

Recommended for use on aluminium, galvanized surface for etching for better adhesion of subsequent primer. It is recommended on M.S. also for better adhesion of coating system.

PHYSICAL CONSTANTS

Colour	Yellow
Finish	Flat
Solids By Volume	Not Relevant
Theoretical Spreading Rate	12 - 13 sq.mtr./ltr. at recommended D.F.T. on smooth and non absorbent surface.
Flash Point	Above 25 deg. C
Drying Characteristics	Drying Characteristics DRY TO TOUCH : 20 - 30 minutes DRY TO HANDLE : 8 hrs. FULLY CURED : Overnight
Shelf Life	9 months (of individual component) - Stored under proper condition of temp. & pressure.
Thinner Recommended	Chemilac G.P. Thinner
Finish / Gloss	Smooth & Matt
Acid Alkali (2%) Resistance	Good
Scratch Hardness	2000 Grams

NOTE

All information gives in this sheet are accurate to the best of our knowledge, no warranty given and no liability is accepted in respect of such information as conditions of applications are beyond our control

USES

For Electric oven, Furnace Boilers, Auto Silencers etc.

NOTE

All information given in this sheet are accurate to the best of our knowledge, no warranty is given and no liability is accepted in

respect of such information as conditions of applications are beyond our control.

CONTACT :

The Chemicals of India

(Prop. Chemilac Paints Pvt. Ltd.)

Plot No 36, Sector 27C, Faridabad-121003. Haryana

Phone : 91-129-2277382, 2277392

Fax : 91-129-2271607

Email : info@chemilac.com

visit us at : www.chemilac.com
