



## STOVING EPOXY PRIMER

Epoxy stoving coating are single pack system having excellent chemical and corrosion resistance. These have advantage over two-pack epoxy system.

1. No risk of pot life
2. Need not to wait for days to get optimum properties

<b>Viscosity</b>	80+ or - 5 sec
<b>S.G</b>	1.35 + or - 0.05
<b>Finish</b>	5 on H.G
<b>Colour</b>	Red/ Grey
<b>Corrosive Resistance (200 hrs. 35 micron DFT)</b>	Passed
<b>Flexibility Adhesive</b>	Very Good
<b>Salt Spray 200 hrs. (35 m)</b>	Passed
<b>Thinner Recommended</b>	Chemilac Stoving Thinner
<b>Flexibility &amp; Adhesion</b>	Passed the test
<b>Resistance to salt spray</b>	Passed
<b>Shelf life</b>	one year

### APPLICATION :

1. Surface should be cleaned, de-rust and degreased before applying
2. Apply Epoxy stoving primer, give 10 minutes flash off period.
3. Stove it 30 minutes at 180 C.

### Notes :

All information gives in this sheet are accurate to the best of our knowledge, no warranty given and no liability is accepted in respect of such information as conditions of applications are beyond our control.

**CONTACT :**

**The Chemicals of India**

(Prop. Chemilac Paints Pvt. Ltd.)

Plot No 36, Sector 27C, Faridabad-121003. Haryana

**Phone :** 91-129-2277382, 2277392

**Fax :** 91-129-2271607

**Email :** [info@chemilac.com](mailto:info@chemilac.com)

visit us at : [www.chemilac.com](http://www.chemilac.com)

---